

Dimensional Stability

Excellent Stability

American Walnut
Reclaimed Heart Pine
Australian Cypress
Teak

Above Average Stability

African Rosewood (Bubinga)
African Teak (Afromosia)
American Cherry
Ash
Santos Mahogany
Tasmanian Oak
Yellow Pine

Average Stability

African Cherry
African Doussie
African Iroko
African Mahogany (Sapele)
African Wenge
Australian Sydney Blue
Bamboo
Birch
Brazilian Cherry
Brazilian Walnut (Ipe)
Canadian Maple
European Maple
Peruvian Walnut (Nogal)
Red Oak
White Oak

Below Average Stability

Australian Jarrah
Beech
Brazilian Chestnut (Cumaru)
Hickory